

Technical Data Sheet

PIR PA6 Regranulate Natural

Product Code: 019007

Recycled Content: 100 % PIR (post-industrial)

Product Description:

019007 PIR PA6 Regranulate Natural comes from post-industrial recycled materials in Europe and is suitable for compounding and extrusion applications.



Physical Property	Value	Units	Test Standard	Test Condition
Tensile modulus	3000	MPa	ISO 527	1 mm/min.
Charpy notched impact strength	24	kJ/m ²	ISO 179/1eA	23°C, cond.
Relative Viscosity	3.20		ISO 307	0.01 g/ml H ₂ SO ₄ , 96%
Viscosity number	187.7	ml/g	ISO 307	0.005 g/ml H ₂ SO ₄ , 96%

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of these data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.