

Technical Data Sheet

PCR PP Regrind Mixed color

Product Code: 260303

Recycled Content: 100 % PCR (post-consumer)

Product Description:

260303 PCR PP Regrind Mixed color comes from post-consumer recycled materials in Europe and is suitable for compounding applications.



Physical Property	Value	Units	Test Condition
Melt Flow Index	20.25	g/10 min	230°C, 2.16 kg
Glass transition (Tg)	8.54	°C	DSC
Crystallization temperature	81.53	°C	DSC
Melting onset	126.02	°C	DSC
Peak melting temperature	166.84	°C	DSC
End melting temperature	180.19	°C	DSC
Enthalpy change	-78.94	J/g	DSC, 25-300°C, 10.0°C/min, N2 50±5 cm3/min
Shape and size	Regrind ~ 10 mm		

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of these data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.