

Technical Data Sheet

PCR ABS Regranulate black

Product Code: 001302



Physical Properties	Value	Units
Density	1.05	g/cm ³
MFI (220°C, 10kg)	20	g/10 min.
HDT A	85	°C
Pellet shape	Pellet	n/a
Grain size	3-6	mm
Melt point	230	°C
Charpy Notched Impact Strength	75	kJ/m ²
Impact strength Izod (23°C)	11	kJ/m ²
Flexural modulus	2100	MPa
Flexural strength	70	MPa
Tensile strength at break	40	MPa

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.