

Technical Data Sheet

PCR ABS Regranulate white

Product Code: 190104



Physical Properties	Value	Units
Density	1.07	g/cm ³
MFI (220°C, 10kg)	20-25	g/10 min.
Flexural modulus	>2300	MPa
IZOD notched at 23°C	14	kJ/m ²
Processing Condition	Value	Units
Pre-Drying	Hot air or desiccant	n/a
Drying temperature	80	°C
Drying time	2-4	h
Melt Temperature Range	210-230	°C
Recommended Melt Temperature	215	°C
Mold Temperature Range	50-70	°C
Recommended Mold Temperature	60	°C

Technical Data Sheet

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.

