Technical Data Sheet

PCR HDPE Regranulate green

Product code: 001402

Physical Properties	Value	Units	Standard
Form	Regranulate	n/a	n/a
Color	Green	n/a	n/a
MFI (230°C,2.16kg)	1.1	g/10 min.	DIN ISO 1133
Density	0.941	g/cm³	DIN ISO 1183
Tensile stress	24.65	MPa	DIN ISO 527
Tensile modulus	n/a	MPa	DIN ISO 527
Flexural stress	16.2	MPa	DIN ISO 178
Flexural modulus	n/a	MPa	DIN ISO 178
Charpy notched impact strength	17.3	kJ/m²	DIN ISO 179

Disclaimer
This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.

Sinox Polymers GmbH
Grünenweg 5-7
DE-28195 Bremen
info@sinox-polymers.com
+49 178 / 8175 168

Handelsregisternummer:
HRB 33699, Amtsgericht Bremen
Ust-IdNr: DE319539787
Geschäftsführer:
Marvin Pfeiffer

Bankverbindung
Deutsche Bank
IBAN:
DE68 2907 0050 0211 0799 00
BIC: DEUTDEHBXXX