

Technical Data Sheet

HDPE Regranulate light grey

Product Code: 014005



Description

PCR 014005 HDPE Regranulate light grey is suitable for blow moulding applications was recovered in Europe.

Physical Properties	Value	Units
Shape	Pellets	n/a
Density	0.947	g/cm ³
MFI (190°C,5kg)	2.48	g/10 min.
Moisture content	< 0.1	%
Ash content	< 2	%
PP-content	< 2	%

Processing

Recommended melt temperature range for blow moulding application: 190°C-210°C

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.