Technical Data Sheet

PCR PC GF12 Regrind with metal

Product Code: 030203

Physical Properties	Value	Units	Standard
MFI (300°C, 1.2kg)	31.3	g/10 min.	ISO 1133
Melting point	162.3	°C	ISO 3146
Glass fiber content	12	%	n/a
Color	light grey	n/a	Visual assessment
Vicat Softening Temperature B/50	142	°C	ISO 75-2

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.

Sinox Polymers GmbH
Grünenweg 5-7
DE-28195 Bremen
info@sinox-polymers.com
+49 178 / 8175 168

Handelsregisternummer:
HRB 33699, Amtsgericht Bremen
Ust-IdNr: DE319539787
Geschäftsführer:
Marvin Pfeiffer

Bankverbindung
Deutsche Bank
IBAN:
DE68 2907 0050 0211 0799 00
BIC: DEUTDEHBXXX