

Technical Data Sheet

PP Regranulate

Product Code: 080304



Description

PCR 080304 PP Regranulate black is suitable for injection moulding and compounding applications and was recovered in Europe. It is Recyclclass certified.

Physical Properties	Value	Units	Test Method
Density	0.93	g/cm ³	ISO 1183
Melt Flow Index (230°C, 2.16kg)	18-23	g/10 min	ISO 1133
Charpy notched impact strength	2.1-2.7	kJ/m ²	ISO 179
Yield stress	27.7	MPa	ISO 527
Tensile strain at break	178.9	%	ISO 527
Softening point, Vicat method 10N	148	°C	ISO 306
Color	Black	n/a	Visual assessment
Shape	Pellets, round	n/a	Visual assessment

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of these data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.