

Technical Data Sheet

PCR PP Regranulate White Color

Product Code: 000619



Description

PCR PP 000619 is a 100% PCR (post-consumer recycled) polypropylene material with a good melt flow rate and good impact resistance, designed for injection molding process.

PCR PP 000619 is made from 100% Post consumer recycling products. These products are manufactured through high quality recycling process, consist of hot washing, melt filtration, pelletization and degassing etc., comply with GRS (Global Recycled Standard).

Applications

Houseware goods	Packaging components
Other injection use	

Special Features

Good impact resistance	Stable MFR suitable for injection molding
------------------------	---

Compliance

RoHS Directive (EU) 2011/65	REACH (224 SVHC)
-----------------------------	------------------

Physical Properties	Value	Units	Test Method
Density	0,913	g/cm ³	ISO 1183
MFR (230°C/ 2,16kg)	18	g/10 min	ISO 1133
Tensile Stress (50mm/min)	25	MPa	ISO 527-2
Tensile Modulus (50mm/min)	1150	MPa	ISO 527-2
Elongation at Break	30	%	ISO 527-2

Technical Data Sheet

Flexural Modulus	1070	MPa	ISO 178
Flexural Strength	32	MPa	ISO 178
Ash Content	1.5	%	ISO 3451-1
Melt Point	160	°C	ISO 11357
Molding Shrinkage	1.55	%	Internal
Charpy Impact Strength, notched (23°C)	7.4	KJ/m ²	ISO 179
Heat Deflection Temperature (0,45MPa)	88	°C	ISO 75-2
Heavy Metals (Rohs)	Cd, Hg, Pb, Cr	-	

Processing Conditions

PCR PP 000619 is easy to process with standard injection moulding machines.

Following parameters should be used as guidelines:

Melt temperature:	180 -210 °C
Holding pressure:	200 – 500 bar
Mould pressure:	60-100 MPa
Mould temperature:	30-50 °C
Molding time:	30-60 s

Shrinkage 1 - 2%, depending on wall thickness and moulding parameters.

Technical Data Sheet

Storage

PCR PP 000619 should be stored in dry conditions at temperatures below 50°C and protected from UV-light. Improper storage can initiate degradation, which results in odor generation and color changes and can have negative effects on the physical properties of this product.

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of these data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.