

Technical Data Sheet

PCR / PIR PVC Regrind hard ex. window profiles

Product Code: 300503



Description: 300503 PVC Regrind hard ex. window profiles comes from post-consumer-recycling window profiles in Europe and is suitable for compounding applications.

| Physical Properties | Value | Units | Standard |
|--------------------------------|-------------|-------------------|-------------|
| Density | 1.48 - 1.55 | g/cm ³ | ISO 1183 |
| VICAT B50 - softening point | 77 - 81 | °C | ISO 306 |
| Thermostability at 200°C | 20 | min. | ISO 179 |
| Charpy impact strength at 23°C | 3 - 7 | kJ/m ² | DIN 53381-C |

Disclaimer

This information contained herein is based on the data available to us and is believed to be correct. However, Sinox makes no warranty, expressed or implied, regarding the accuracy of this data or the results to be obtained from the use thereof. Each user of the products shall convince himself through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its particular purpose.